

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-210313

(43)Date of publication of application : 02.08.2000

(51)Int.Cl.

A61F 2/28
A61L 27/00

(21)Application number : 11-012301

(71)Applicant : KOBE STEEL LTD

(22)Date of filing : 20.01.1999


(72)Inventor : KOKUBO TADASHI
SUZUKI JUN
SUZUKI TETSUO
SASAKI YOSHIO
MATSUSHITA TOMIHARU

(54) BONE SUBSTITUTIVE MATERIAL HAVING EXCELLENT BIOAFFINITY

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a bone substitutive material which is uniformly formed with a layer exhibiting good bioaffinity in the rugged portions of a base material by a simple method and exhibits a sufficient shearing strength.

SOLUTION: This bone substitutive material is formed with ruggedness on the surface of the base material made of titanium or titanium alloy which is a bonding surface to the vital tissue. The root diameter W of the projecting parts of the ruggedness is ≥ 40 μm in average. An alkali titanate layer 21 having ≥ 35 atm.% in oxygen concentration is formed across a depth of 0.5 to 2 μm in the ruggedness. The layer 21 has the good bioaffinity. The core portions of the projecting parts are titanium or titanium alloy portions 12 and, therefore, thin film the strength of the projecting parts is sufficiently assured and, then, the possibility that the projecting parts are dislodged is extremely little in spite of the exertion of external force.



LEGAL STATUS

[Date of request for examination]

20.09.2002

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the
examiner's decision of rejection or application
converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of
rejection]

[Date of requesting appeal against examiner's decision]

of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office